

VUKA COAT 301

DESCRIPTION

Vuka Coat 301 is a solvent free coloured multi component hi build epoxy coating.

USES

Floor coating for general industry, prisons, ablution blocks, workshops, food processing plants, hospitals, schools, public buildings, pharmaceutical plants, cosmetic plants and the like.

BENEFITS

Solvent free – safe to apply
 Economical, durable and abrasive resistant
 Good chemical resistance
 Seamless and hygienic
 Standard colour range

PROPERTIES

The following are typical properties achieved at 20C and 50% relative humidity.

Light traffic @ 20C	24hrs
Heavy traffic @ 20C	2 Days
Full cure @ 20C	7 Days
Theoretical coverage	4m ² /Litre per coat
Fire Resistance	Class 4 – SANS 10177 : Part 4 : 2005
Slip Resistance	BS EN 13036-4:2011. Typical values for Four-S Rubber. Dry 81 Wet 36
Impact Resistance	ISO6272-1:2011 1kg weight >1.8m 2kg weight >1.5m
Abrasion Resistance	SANS 1149:2012
Thermal Resistance	Tolerant of sustained temperatures of 65 C
Water Permeability	Nil – Contest test. (Impermeable)
Compressive Strength:	>70 N/mm ² SM SABS 863:1994
Flexural Strength:	>25 N/mm ² SM SABS 864:1994
Tensile Strength:	>15 N/mm ² SM SABS 1253:1994



Product colours will differ slightly and it is best to obtain actual colour samples where required. See colour chart for full range of standard colours.

VUKA COAT 301

Bond Strength: Greater than cohesive strength of 25N/mm² concrete > 1.5 N/mm² Proceq Dyna

SURFACE REQUIREMENTS

Concrete / Grano surfaces must have a minimum compressive strength of 25N/mm², a minimum tensile strength of 1.5N/mm², be at least 40mm thick. The substrate must be dry, free of oils waxes fats and other contaminants. Vacu-blasting, scarification, abrasive grinding followed by vacuum cleaning is preferred. The surface must show open pores throughout with exposed aggregate. **Acid etching is not acceptable.**

MIXING

Kit components are pre-weighed for optimum performance therefore never split or proportion a kit. Pre stir base and activator. Add the entire activator to the base and using a slow speed drill (+300rpm) fitted with a spiral blade mix for 3 minutes.

APPLICATION

Can be applied by squeegee, serrated trowel and then back rolled with short nap roller. Observe the overcoat times.

CURING

At 25C constant, excessive traffic, aqueous contact and exposure to aggressive chemicals should only take place after 7 days when full cure has been achieved. At 10C constant, full cure would take a minimum of 12 days.

OPTIONAL FINISHES

Standard finish: Gloss
Optional finish
Matt sealer coat – Vuka Super Satin
LAS - Light Anti Slip
MAS - Medium Anti Slip
HAS – Heavy Anti Slip

CHEMICAL RESISTANCE

For chemical resistance information please contact our Technical Department

STORAGE

12 Months from date of production if stored in original sealed containers in dry conditions at temperatures between +5C and +30C.

HEALTH AND SAFETY

Use of basic principles of industrial hygiene and protective clothing such as gloves, goggles, masks will enable the product to be used safely. Splashes into eyes should be washed immediately with clear water and medical advice sought.

BILL OF QUANTITY DESCRIPTIONS

Contact Vuka Floors for a detailed bill description to suit your specific requirements.

MODEL SPECIFICATION

Prepare surface and prime with Vuka Prime 102 at 4m²/Litre then apply 2 coats of Vuka Coat 301 at 4m²/Litre per coat in strict accordance with the technical data obtainable from Vuka Floors. All work to be done by Vuka Floors approved applicators.

REFERENCE PANEL

A reference sample should be installed by the applicator prior to the start of the contract to ensure correct coverage, workmanship and acceptance by the client as a standard for the project.

FURTHER INFORMATION

This product will change in colour over time. Especially when subject to high levels of UV and or chemical attack. For best colour stability consult our technical department. This does not compromise the products physical and chemical resistance characteristics.

VUKA COAT 301

Vuka Floors products are guaranteed against defective materials and manufacture and are sold subject to its Terms and Conditions which may not be overridden in any other legal documentation.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience at the date of issuance it is subject to change without prior notice. User must contact Vuka Floors to verify correctness before specifying or ordering. No warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Figures given for consumption / spread rates are theoretical and do not allow for additional materials due to surface profile, porosity, variations in level and wastage etc.