

VUKA SPEC

DESCRIPTION

Vuka Spec is a modern decorative, solvent free, self-leveling epoxy system applied at 1mm thickness. Vuka Spec exhibits a speckled finish with good UV, abrasion, and chemical resistance.


USES

Vuka Spec is ideal for areas subject to constant wear but requiring a smooth easily cleanable decorative surface. Suitable in commercial and retail environments as well as lobbies, showrooms, hotels, hospitals, canteens, schools, warehouses, laboratories, electronic, aerospace, automotive, pharmaceutical and printing plants.


BENEFITS

- Decorative modern speckled finish
- Available in Gloss or Matt
- Solvent free – safe to apply - odourless
- Hygienic –easy to clean – seamless
- Liquid proof
- Hard wearing – abrasion resistant
- Excellent chemical resistance
- Range of standard colours
- Self smoothing

ILLUSTRATION



1. Select your epoxy colour



2. Select spec size

● 1mm = LIGHT ◈ 2mm = BOLD

3. Select spec colours



Vuka Spec can be applied in any of the Standard colours as well as special on request. Product

VUKA SPEC

colours will differ slightly and it is best to obtain actual colour samples where required.

TYPICAL PROPERTIES

The following are typical properties achieved at 20C and 50% relative humidity.

Light traffic @ 20C	24hrs
Heavy traffic @ 20C	2 Days
Full cure @ 20C	7 Days
Theoretical coverage	1m ² /Litre
Fire Resistance	Class 4 – SANS 10177 : Part 4 : 2005
Slip Resistance	BS EN 13036-4:2011. Typical values for Four-S Rubber. Dry 81 Wet 36
Impact Resistance	ISO6272-1:2011 1kg weight >1.8m 2kg weight >1.5m
Abrasion Resistance	SANS 1149:2012
Thermal Resistance	Tolerant of sustained temperatures of 65 C
Water Permeability	Nil – Contest test. (Impermeable)
Compressive Strength:	>70 N/mm ² SM SABS 863:1994
Flexural Strength:	>25 N/mm ² SM SABS 864:1994
Bond Strength:	Greater than cohesive strength of 25N/mm ² concrete > 1.5 N/mm ² Proceq Dyna
Tensile Strength:	>15 N/mm ² SM SABS 1253:1994

SURFACE REQUIREMENTS

Concrete / Grano surfaces must have a minimum compressive strength of 25N/mm², a minimum tensile strength of 1.5N/mm², be at least 40mm thick. The substrate must be dry, free of oils waxes fats and other contaminants. Vacu-blasting, scarification, abrasive grinding followed by vacuum cleaning is preferred. The surface must show open pores throughout with exposed aggregate. **Acid etching is not acceptable.**

MIXING

Do not split kits. Vuka Coat 300 to be mixed and installed at 3m²/Litre as per technical datasheet. Porous surfaces may require a second coat.

Vuka Spec – pre stir base and activator. Add the entire activator to the base and mechanically mix for 3 minutes. Be sure to run the paddle along the container sides and bottom to blend in unmixed components which might cling to walls. Vuka Super Satin for matt finish to be mixed as supplied and installed as per technical datasheet.

APPLICATION

Spread the mixed Vuka Spec to the required 1mm thickness with a 3mm notched rake and allow to level then de-aerate with a spiked roller after 10 minutes to ensure the release of any entrapped air. Application with tools other than a 3mm notched rake may affect consistency of the Spec.

OPTIONAL FINISHES

Standard finish: Gloss
Recommended / Optional finish
Matt sealer coat – Vuka Super Satin

CURING

At 25C constant, excessive traffic, aqueous contact and exposure to aggressive chemicals should only take place after 7 days when full cure has been achieved. At 10C constant, full cure would take a minimum of 12 days.

CHEMICAL RESISTANCE

For chemical resistance information please contact our Technical Department

STORAGE

12 Months from date of production if stored in original sealed containers in dry conditions at temperatures between +10 C and +30 C.

VUKA SPEC

HEALTH AND SAFETY

Use of basic principles of industrial hygiene and protective clothing such as gloves, goggles, masks will enable the product to be used safely. Splashes into eyes should be washed immediately with clear water and medical advice sought.

Figures given for consumption / spread rates are theoretical and do not allow for additional materials due to surface profile, porosity, variations in level and wastage etc.

BILL OF QUANTITY DESCRIPTIONS

Contact Vuka Floors for a detailed bill description to suit your specific requirements.

MODEL SPECIFICATION

Prepare surface install Vuka Spec solvent free epoxy at 1mm thickness in strict accordance with the technical data obtainable from Vuka Floors. All work to be done by Vuka Floors approved applicators.

REFERENCE PANEL

A reference sample should be installed by the applicator prior to the start of the contract to ensure correct coverage, workmanship and acceptance by the client as a standard for the project.

FURTHER INFORMATION

This product will change in colour over time. Especially when subject to high levels of UV and or chemical attack. For best colour stability consult our technical department. This does not compromise the products physical and chemical resistance characteristics.

Vuka Floors products are guaranteed against defective materials and manufacture and are sold subject to its Terms and Conditions which may not be overridden in any other legal documentation.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience at the date of issuance it is subject to change without prior notice. User must contact Vuka Floors to verify correctness before specifying or ordering. No warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.